

PARADOR

Laminate Trendtime 4

Product quality		Tolerances	
Formats	1285 x 400 x 8 mm	Squareness of the elements ($\leq 0.50\text{mm}$)	$\leq 0,10\text{mm}$
Packaging	Pack: 5 elements / 2.57 m ² / 18.93 kg Pallet: 28 packs / 71.96 m ² / 545 kg	Determination of Linearity ($\leq 0.30\text{ mm}$)	$\leq 0,10\text{ mm/m}$
Guarantee (according Parador guarantee conditions)		Surface flushness	(average $\leq 0.15\text{ mm}$) (max. $\leq 0.15\text{ mm}$)
Domestic area	Lifetime		(average $\leq 0.05\text{ mm}$) (max. $\leq 0.10\text{ mm}$)
Commercial area	5 years	Opening between installed elements	(average $\leq 0.15\text{ mm}$) (max. $\leq 0.20\text{ mm}$)
Notes	- not suitable for all-over adhesion - cleaning an maintenance see instructions - technical changes reserved	Block alignment	$\pm 2\text{ mm}$



Classification		Test method	Rating
	Utility class 23 domestic areas with intensive use	EN 13329	Living room, hall, kitchen, home office
	Utility class 32 commercial areas with medium use	EN 13329	Classrooms, small offices, shops
	Abrasion	EN 13329, Annex E	AC 4 ($\geq 4.000\text{ rev.}$)
	Impact resistance	EN 13329, Annex F	IC 2
	Reaction to fire	EN 13501-1	C _{fl} s1
	Slip resistance	EN 13893 EN 14041	$\mu \geq 0,35$ DS
	Staining resistance	EN 438-2	Category 1+2: level 5 Category 3: level 4/5
	Cigarette resistance	EN 438-2	level 4
	Light fastness	EN ISO 4892-2	Blue wool scale: Stage ≥ 6
	Resistance to roller castor chairs	EN 425	Type W, no visible changes
	Electrical behaviour	EN 1815	$\leq 2\text{ kV}$
	Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN 12664	0,048 m ² *K/W
	Moving a furniture leg	EN 424	No visible changes
	Indentation-residual	EN ISO 24343-1	$\leq 0,05\text{mm}$
	Formaldehyde emission (E1 = 0.1 ppm)	EN 717-1	$\leq 0,05\text{ ppm}$
	Locking strength of mechanically assembled panels	ISO 24334	$> 1\text{ kN/m}$ (long side) $> 2\text{ kN/m}$ (short side)
	Acoustical - Impact noise reduction	ISO 717-2	14 dB (on Akustik-Protect 100)
	Dimensional stability	EN 13329	$\leq 0,9\text{mm}$
	Thickness swelling	EN 13329, Annex G ($\leq 18\%$)	$\leq 12\%$
	Surface soundness	EN 433	$\geq 1,8\text{ N/mm}^2$
	Scratch resistance	EN 438	Level 4
	Slip resistance on an inclined plane	DIN 51130	Depending on structure: -/R 9/R10
	Disposal		EAK-Code-number 20 01 38
	Aqua Proof enables installation in wet rooms with up to one hour protection against standing water (please see installation instructions).		

Changed:	QMB Parador	File:	20180901_PA_TDS_Laminat_Trendtime-4_EN
Date:	01.01.2014	Latest update at:	www.parador.eu/service/catalogues-downloads/technical-data-sheets
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.09.2018