

MARDOM DECOR

MARDOM DECOR

Ratajska 11a Str.
91-231 Lodz
PL
www.mardomdecor.com

contact person: Magdalena Kowalska
tel.: +48 42 678 67 86
fax: +48 42 678 67 87
e-mail: m.kowalska@mardom-sp.pl

ProFoam[®]

TECHNICAL SPECIFICATION

CHARACTERISTICS

DENSITY:	ca. 220 kg/m ²
COMPOSITION:	polyurethane polyol prepare (42%): alkylaminopoluol, diethylmethylbenzendiamine, alkylaminocarbonsaureamide difenylmethane - diisocyanate (58%). The product is free of CFC, ozone depletion factor: 0 The product is free of asbestos. The product is free of cyanides.
HARDNESS:	ca. 35 Shore D (can be variable)
THICKNESS:	Variable. 8 mm - 50 mm
SURFACE:	Covered with one component paint based on methylethylketone.
TOXICITY:	The product itself has a low oral toxicity. The inhalation toxicity of the foam dust (inert dust) is considered to be low.
FIRE RESISTANCE:	The standard material is not flame retardant. Fire standard E. Can be treated with fire retardant paint to obtain fire standard C-S2, d 0

MARDOM DECOR

MARDOM DECOR

Ratajska 11a Str.
91-231 Lodz
PL
www.mardomdecor.com

contact person: Magdalena Kowalska
tel.: +48 42 678 67 86
fax: +48 42 678 67 87
e-mail: m.kowalska@mardom-sp.pl

ProFoam®

TECHNICAL SPECIFICATION

TECHNICAL DATA

1.1. MATERIAL:	integral foam
1.2 DENSITY:	$\pm 220 \text{ kg/m}^3$
1.3 HARDNESS:	over 30 Shore D
1.4 OZONE DEPLETION FACTOR:	0 (cfc free, waterblown)
1.5 TEMPERATURE RANGE	
WITHOUT DEGRADATION:	-20°C/+80°C
1.6 IGNITION TEMPERATURE	Higher than 350°C
1.7 LINEAR THERMAL	
EXPANSION COEFFICIENT:	40 - 60. 10 - 6 m/k m
1.8 FIRE RESISTANCE:	It is possible to make poliurethane flame retardant.
1.9 PRIMER:	One component paint. Will accept any kind of good quality paint.

CHARACTERISTICS

2.1 CHEMICAL PROPERTIES:	Does not deteriorate. Resistant to most common solvents and moisture.
2.2 PHYSICAL PROPERTIES:	Shock and split resistant.
2.3 INFLUENCE OF TIME:	Dimensionally stable, will not alter with time.
2.4. INFLUENCE OF HUMIDITY:	Water absorption (after 24 hours): <0,1%. No influence on the mechanical properties.
2.5. INFLUENCE OF SOUND:	Polyurethane is acoustically neutral.
2.6. INFLUENCE OF LIGHT AND SUN:	Not UV - resistant. UV resistant after final painting.
2.7. TOXICITY:	The product has low oral toxicity. The majority of opinions suggest that the inhalation toxicity of the foam dust is low. Some authors consider that the foam dust should't be regarded merely as an inert 'nuisance dust'. Indoor VOC (Volatile Organic Compounds) Inhalation risk very low emission A+ (VOC 0%)